



AMENDMENTS TO THE CLAIMS

1. (Original) A cement admixture
which comprises a polycarboxylic acid copolymer having a polyalkylene glycol side chain,
said polycarboxylic acid copolymer being constituted of two or more species of copolymers
with different acid values, and
at least one of said two or more species of copolymers with different acid values having an
oxyalkylene group containing 3 or more carbon atoms.
2. (Original) The cement admixture according to Claim 1,
wherein the ratio of the acid value of said two or more species of copolymers is 1.2 to 5.
3. (Original) A cement admixture
which comprises a polycarboxylic acid copolymer having a polyalkylene glycol side chain
containing an oxyalkylene group having 3 or more carbon atoms,
said polycarboxylic acid copolymer being constituted of two or more species of copolymers
with a weight average molecular weight of 20000 or less.
4. (Currently Amended) The cement admixture according to Claim 1, ~~2 or 3~~,
wherein said copolymer has a site represented by the following formula (1);




in the formula, R^1 and R^2 may be the same or different and each represents a hydrogen atom or a methyl group; x represents a number of 0 to 2, y represents 0 or 1; R^3Os may be the same or different and each represents an oxyalkylene group having 2 to 18 carbon atoms, and 0.01 to 49 mole % of an average molar number of addition of the oxyalkylene group is an oxyalkylene group having 3 to 18 carbon atoms; R^4 represents a hydrogen atom or a hydrocarbon group having 1 to 30 carbon atoms; and m is an average molar number of addition of the oxyalkylene group, and represents a number of 3 to 300,

and a site represented by the following formula (2);




in the formula, R^5 and R^6 may be the same or different and each represents a hydrogen atom or a methyl group; z represents a number of 0 to 2; w represents 0 or 1; R^7 represents a hydrogen atom or a hydrocarbon group having 1 to 30 carbon atoms; and n is an average molar number of addition of an oxyethylene group, and represents a number of 1 to 300.

5. (Original) A cement admixture comprising a polycarboxylic acid copolymer, wherein said polycarboxylic acid copolymer has the site represented by the following formula (1);



in the formula, R^1 and R^2 may be the same or different and each represents a hydrogen atom or a methyl group; x represents a number of 0 to 2; y represents 0 or 1; R^3O s may be the same or different and each represents an oxyalkylene group having 2 to 18 carbon atoms, and 0.01 to 49 mole % of an average molar number of addition of the oxyalkylene group is an oxyalkylene group having 3 to 18 carbon atoms; R^4 represents a hydrogen atom or a hydrocarbon group having 1 to 30 carbon atoms; and m is an average molar number of addition of the oxyalkylene group, and represents a number of 3 to 300,

and the site represented by the following formula (2);




in the formula, R^5 and R^6 may be the same or different and each represents a hydrogen atom or a methyl group; z represents a number of 0 to 2; w represents 0 or 1; R^7 represents a hydrogen

atom or a hydrocarbon group having 1 to 30 carbon atoms; and n is an average molar number of addition of an oxyethylene group, and represents a number of 1 to 300.

6. (Original) The cement admixture according to Claim 5, wherein a mole ratio of the site represented by the formula (1) and the site represented by the formula (2) in said polycarboxylic acid copolymer: (A)/(B) is 1/99 to 99/1.

7. (Currently Amended) The cement admixture according to Claim 5 ~~or 6~~, wherein said polycarboxylic acid copolymer has a site in which R³O in the formula (1) is the following formula (6):




in the formula, R⁸ represents an alkylene group having 3 to 18 carbon atoms; r and q are average molar numbers of addition of oxyethylene groups, and each represents a number of 0 to 300, provided that one of r and q is 0, the other is a number of 2 to 300; p represents an average molar number of addition of the oxyalkylene group, and is a number of 1 to 50, and r+p+q is a number of 3 to 300,

and the site represented by the formula (2).

8. (Original) The cement admixture according to Claim 7, wherein a mole ratio of the site in which R³O in the formula (1) is the formula (6) and the site represented by the formula (2): (C)/(B) is 1/99 to 99/1.


9. (New) The cement admixture according to Claim 2, wherein said copolymer has a site represented by the following formula (1);



in the formula, R¹ and R² may be the same or different and each represents a hydrogen atom or a methyl group; x represents a number of 0 to 2, y represents 0 or 1; R³O's may be the same or

different and each represents an oxyalkylene group having 2 to 18 carbon atoms, and 0.01 to 49 mole % of an average molar number of addition of the oxyalkylene group is an oxyalkylene group having 3 to 18 carbon atoms; R^4 represents a hydrogen atom or a hydrocarbon group having 1 to 30 carbon atoms; and m is an average molar number of addition of the oxyalkylene group, and represents a number of 3 to 300,


and a site represented by the following formula (2);



in the formula, R^5 and R^6 may be the same or different and each represents a hydrogen atom or a methyl group; z represents a number of 0 to 2; w represents 0 or 1; R^7 represents a hydrogen atom or a hydrocarbon group having 1 to 30 carbon atoms; and n is an average molar number of addition of an oxyethylene group, and represents a number of 1 to 300.


10. (New) The cement admixture according to Claim 3,

wherein said copolymer has a site represented by the following formula (1);




in the formula, R^1 and R^2 may be the same or different and each represents a hydrogen atom or a methyl group; x represents a number of 0 to 2, y represents 0 or 1; R^3O s may be the same or different and each represents an oxyalkylene group having 2 to 18 carbon atoms, and 0.01 to 49 mole % of an average molar number of addition of the oxyalkylene group is an oxyalkylene group having 3 to 18 carbon atoms; R^4 represents a hydrogen atom or a hydrocarbon group having 1 to 30 carbon atoms; and m is an average molar number of addition of the oxyalkylene group, and represents a number of 3 to 300,

and a site represented by the following formula (2);



in the formula, R⁵ and R⁶ may be the same or different and each represents a hydrogen atom or a methyl group; z represents a number of 0 to 2; w represents 0 or 1; R⁷ represents a hydrogen atom or a hydrocarbon group having 1 to 30 carbon atoms; and n is an average molar number of addition of an oxyethylene group, and represents a number of 1 to 300.

11. (New) The cement admixture according to Claim 6,
 wherein said polycarboxylic acid copolymer has a site in which R³O in the formula (1) is the following formula (6):



in the formula, R⁸ represents an alkylene group having 3 to 18 carbon atoms; r and q are average molar numbers of addition of oxyethylene groups, and each represents a number of 0 to 300, provided that one of r and q is 0, the other is a number of 2 to 300; p represents an average molar number of addition of the oxyalkylene group, and is a number of 1 to 50, and r+p+q is a number of 3 to 300,

and the site represented by the formula (2).

12. (New) The cement admixture according to Claim 11,
 wherein a mole ratio of the site in which R³O in the formula (1) is the formula (6) and the site represented by the formula (2): (C)/(B) is 1/99 to 99/1.